



TECHNICAL DATA SHEET

PRODUCT	AXEL MC – 12
TDS Number	QA/FPS/0030
Date of Issue	25 th June, 2005
Version Number	04

AXEL MC – 12

PRODUCT DESCRIPTION

This is a specially formulated grade of solvent based Cobalt Octoate 3% which is most suitable for acceleration of unsaturated polyester resins. In addition to the below, we can also offer the same system having metal contents of 2 %, 6 % & 12 % on regular basis.

Properties	Test Methods	Specification
Appearance	VISUAL	Clear liquid
Color	QA/TMM/005	Dark Violet
Specific Gravity at 30°C	QA/TMM/010	0.83 ± 0.03
Viscosity (Ford Cup B4) at 30°C, Seconds	QA/TMM/006	15 max
Non-volatile matters at 120°C 1hr, % w/w	QA/TMM/013	NA
Metal content as %Co	QA/TMM/026	12.0 ± 0.2
MTO Tolerance	QA/TMM/024	1:19

For more information please call (91-22) 5591-2881 or email aryavart@vsnl.com

Typical values are representative of production and may vary from time to time. All information to the best of our knowledge and belief is accurate and reliable as on the date of compilation. Moreover no warranty or guarantee is made as to the accuracy, reliability or completeness nor do we offer any warrant against patent infringement. It is the users responsibility to ascertain the suitability of this information for his or her use. Sampling and Testing procedures in effect at the time of production will be used for certification and we reserve the right to use any test method in certifying the material.