



TECHNICAL DATA SHEET

PRODUCT	CALCIUM OCTOATE 3%
TDS Number	QA/FPS/0009
Date of Issue	25 th June, 2005
Version Number	04

CALCIUM OCTOATE 3%

PRODUCT DESCRIPTION

Calcium is an auxiliary drier. Alone it does not help drying, but in combination with Cobalt or Manganese, Calcium can replace Lead, particularly in baking finishes.

Calcium is also used to stabilize Lead in water sensitive finishes or in such finishes where free acid is present e.g. alkyds of high acid value. The normal usage level of Calcium varies from 0.02 to 0.2% of the metal.

ARYADRY CALCIUM is available as solution in MTO in various concentrations.

Properties	Test Methods	Specification
Appearance	VISUAL	Clear Liquid
Color (Gardner unit)	QA/TMM/005	4 max
Specific Gravity at 30°C	QA/TMM/010	0.86 ± 0.03
Viscosity (Ford Cup B4) at 30°C, Seconds	QA/TMM/006	15 max
Non-volatile matters at 120°C 1hr, % w/w	QA/TMM/013	NA
Metal content as % Ca	QA/TMM/026	3.0 ± 0.2
MTO Tolerance	QA/TMM/024	1:19

For more information please call (91-22) 5591-2881 or email aryavart@vsnl.com

Typical values are representative of production and may vary from time to time. All information to the best of our knowledge and belief is accurate and reliable as on the date of compilation. Moreover no warranty or guarantee is made as to the accuracy, reliability or completeness nor do we offer any warrant against patent infringement. It is the users responsibility to ascertain the suitability of this information for his or her use. Sampling and Testing procedures in effect at the time of production will be used for certification and we reserve the right to use any test method in certifying the material.