



TECHNICAL DATA SHEET

PRODUCT	INSTABEX C – 900
TDS Number	QA/FPS/019
Date of Issue	1 st September, 2005
Version Number	01

INSTABEX C – 900

PRODUCT DESCRIPTION

Over a period of time, **Aryavart's** research had proved that if various stabilizers are produced in controlled conditions and complexed, the one-pack thus formed, gives better results than commodity stabilizers. The following range of **Stabilizer-Lubricant One-Packs** are offered in flake form and avoids dusting.

This is top of the line product recommended for IS pipes to be produced on high out put new machines. It gives excellent results even with as low dosage as 1.8 to 2.0 phr!

Properties	Test Methods	Specification
Appearance	QA/TMM/026	Off White Creamy Flakes
Metal Content as % Pb	QA/TMM/014	27.00 to 31.00
Metal Content as % PbO	QA/TMM/014	29.08 to 33.39
Specific Gravity	QA/TMM/010	1.20 to 1.40
%Moisture Content	QA/TMM/009	0.50 Max
Soft. Point (°C)	QA/TMM/019	90 to 105

For more information please call (91-22) 5591-2881 or email aryavart@vsnl.com

Typical values are representative of production and may vary from time to time. All information to the best of our knowledge and belief is accurate and reliable as on the date of compilation. Moreover no warranty or guarantee is made as to the accuracy, reliability or completeness nor do we offer any warrant against patent infringement. It is the users responsibility to ascertain the suitability of this information for his or her use. Sampling and Testing procedures in effect at the time of production will be used for certification and we reserve the right to use any test method in certifying the material.