



## TECHNICAL DATA SHEET

PRODUCT	<b>INSTABEX C – 99</b>
TDS Number	QA/FPS/016
Date of Issue	1 <sup>st</sup> September, 2005
Version Number	01

### INSTABEX C – 99

#### PRODUCT DESCRIPTION

Over a period of time, **Aryavart's** research had proved that if various stabilizers are produced in controlled conditions and complexed, the one-pack thus formed, gives better results than commodity stabilizers. The following ranges of Stabilizer-Lubricant One-Packs are offered in flake form and avoid dusting.

This was the first in the Aryavart's Stab-Lube One-Pack series. This is basically recommended for old generation machines, which requires high lubrication along with good thermal stability.

Properties	Test Methods	Specification
Appearance	QA/TMM/026	Off White Creamy Flakes
Metal Content as % Pb	QA/TMM/014	36.00 to 39.00
Metal Content as % PbO	QA/TMM/014	38.77 to 42.01
Specific Gravity	QA/TMM/010	1.40 to 1.60
%Moisture Content	QA/TMM/009	0.50 Max
Soft. Point (°C)	QA/TMM/019	90 to 105

For more information please call (91-22) 5591-2881 or email [aryavart@vsnl.com](mailto:aryavart@vsnl.com)

Typical values are representative of production and may vary from time to time. All information to the best of our knowledge and belief is accurate and reliable as on the date of compilation. Moreover no warranty or guarantee is made as to the accuracy, reliability or completeness nor do we offer any warrant against patent infringement. It is the users responsibility to ascertain the suitability of this information for his or her use. Sampling and Testing procedures in effect at the time of production will be used for certification and we reserve the right to use any test method in certifying the material.