



TECHNICAL DATA SHEET

PRODUCT	LEAD OCTOATE 36%
TDS Number	QA/FPS/0079
Date of Issue	25 th June, 2005
Version Number	04

LEAD OCTOATE 36%

PRODUCT DESCRIPTION

Lead is the most important auxiliary through drier. It is used with active driers like Cobalt and it promotes thorough drying by virtue of its polymerizing effect. **ARYADRY LEAD** promotes hard thorough drying through out the entire film, with out effecting flexibility. Along with Lead, use of a small amount of Calcium and active drier like Cobalt will be desirable. For internal & moderate external temp, these auxiliary driers work well with common active driers. Lead may not be used in aluminum paint where it interferes with leafing and has to be avoided in fume resistant paints as well. Govt. legislation now limits the lead content in residential paints to 0.86%. ARYADRY LEAD is available as stable solution in MTO in various concentrations.

Properties	Test Methods	Specification
Appearance	VISUAL	Clear liquid
Color (Gardner unit)	QA/TMM/005	6 G
Specific Gravity at 30°C	QA/TMM/010	1.36 ± 0.05
Viscosity (Ford Cup B4) at 30°C, Seconds	QA/TMM/006	180 max
Non-volatile matters at 120°C 1hr, % w/w	QA/TMM/013	NA
Metal content as %Pb	QA/TMM/026	36.0 ± 0.5
MTO Tolerance	QA/TMM/024	1:19

For more information please call (91-22) 5591-2881 or email aryavart@vsnl.com

Typical values are representative of production and may vary from time to time. All information to the best of our knowledge and belief is accurate and reliable as on the date of compilation. Moreover no warranty or guarantee is made as to the accuracy, reliability or completeness nor do we offer any warrant against patent infringement. It is the users responsibility to ascertain the suitability of this information for his or her use. Sampling and Testing procedures in effect at the time of production will be used for certification and we reserve the right to use any test method in certifying the material.