



TECHNICAL DATA SHEET

PRODUCT	MANGANESE OCTOATE 6%
TDS Number	QA/FPS/0101
Date of Issue	25 th June, 2005
Version Number	04

MANGANESE OCTOATE 6%

PRODUCT DESCRIPTION

Manganese Activates oxidation and polymerization and provides surface and thorough drying. In combination with Lead, Manganese may partially replace Cobalt. For hard & durable finishes, Manganese is the desirable drier. It is also effective in baking finishes.

The amount of Manganese used may vary from 0.05 to 0.2% in combination with Lead / Zirconium and Cobalt. Manganese is used in fireside chemicals along with Copper Naphthanate.

ARYADRY MANGANESE is available as solution in MTO in various concentrations.

Properties	Test Methods	Specification
Appearance	VISUAL	Clear liquid
Color	QA/TMM/005	Reddish Brown
Specific Gravity at 30°C	QA/TMM/010	0.89 ± 0.03
Viscosity (Ford Cup B4) at 30°C, Seconds	QA/TMM/006	35 max
Non-volatile matters at 120°C 1hr, % w/w	QA/TMM/013	NA
Metal content as % Mn	QA/TMM/026	6.0 ± 0.2
MTO Tolerance	QA/TMM/024	1:19

For more information please call (91-22) 5591-2881 or email aryavart@vsnl.com

Typical values are representative of production and may vary from time to time. All information to the best of our knowledge and belief is accurate and reliable as on the date of compilation. Moreover no warranty or guarantee is made as to the accuracy, reliability or completeness nor do we offer any warrant against patent infringement. It is the users responsibility to ascertain the suitability of this information for his or her use. Sampling and Testing procedures in effect at the time of production will be used for certification and we reserve the right to use any test method in certifying the material.